











Mohizol® Black Series V.S. Based

60°C			1/1 Standard Depth %	Process Suitability						Light Source ISO 105 E02		Washing ISO3	Perspiration ISO 105 E04				Rubbing Fastness ISO 105 X12		Chlorinated Water ISO 105 E02	Dischargeability
				Warm Exhaust	Cold Pad Batch	Pad Dry Pad Steam	Pad Dry Steam	Econtrol	Solubility (g/l) 30°C	1/6	1/1		Acidic		Alkaline		Dry	Wet		
													E	S	E	S				
				2.00%	8.00%															
Black WNN Conc			2/1 6	S	S	S	S	S	200	-	4	4-5	4	4	4	4	4	3	3-4	D
Black WRS-XL			2/1 6	S	S	S	S	S	200	-	4	4	3-4	3-4	3-4	3-4	4	3	3-4	D
Supra Black N			2/1 6	S	S	S	S	S	200	-	4	4-5	4	4	4	4	4	3	3-4	D
Jet Black N			2/1 6	S	S	S	S	S	200	-	4	4	3-4	3-4	3-4	3-4	4	3	3-4	D
Deep Black G			2/1 6	S	S	S	S	S	200	-	4	4-5	4	4	4	4	4	3	3-4	D

- Mohizol® Vinyl Sulphone Black Series is available in a variety of different tones from the Greenest to the Reddest hues to suit the customers desired shade, application and fastness properties.

S = Suitable
NS = Not Suitable

LS = Less Suitable
D = Dischargeable

ND = Not Dischargeable
PD = Partially Dischargeable